

SILICON ETCHING APPARATUS USING XeF_2

Technical Field

5 The present invention generally relates to a silicon etching apparatus and, more particularly, to a silicon etching apparatus using XeF_2 .

Background Art

 There are a variety of etching reagents used for silicon bulk etching to accurate dimensions, ranging from a liquid type etchant such as ethylene diamine pyrocatechol
10 (EDP) and KOH to high energy plasma type etchants based on Cl_2 or SF_6 gases. These etching reagents may provide much flexibility and controllability in the manufacture of accurately defined microstructures but have a limitation on use due to the limited selectivity with respect to general materials such as photoresist or oxide commonly used as a masking layer in the etching process.

15 Xenon difluoride (hereinafter, referred to as " XeF_2 ") is a silicon etching reagent in a dry gas phase which presents several advantages over the above silicon etching reagents. XeF_2 is a white solid at the room temperature under the atmospheric pressure and sublimates at the room temperature (25 °C) under a pressure less than 3.8 Torr. An etching method using sublimated XeF_2 has a high selectivity to photoresist, oxide or aluminum
20 layers and enables etching silicon in the gas phase, thus preventing the resulting structure adhering to the substrate. Also, such an etching method enables rapid etching of the bottom surface of a large-sized silicon structure due to an isotropic etching characteristic and a high etching rate of several $\mu\text{m}/\text{min}$. This etching method using XeF_2 alone neither forms a polymer layer nor leaves other contaminants on the etched surfaces.

25 A conventional silicon etching apparatus using XeF_2 is composed of a loading

chamber for loading XeF_2 , an expansion chamber for collecting sublimated XeF_2 gas, and an etching chamber for performing an etching process.

Several conventional XeF_2 -based silicon etching apparatuses of the above structure involve some problems as follows:

5 First, during the silicon etching process using XeF_2 , air moisture existing in the etching apparatus associates fluorine with hydrogen to form hydrofluoric acid(HF), which may damage a silicon oxide layer used as a profile protecting layer of the silicon. It is thus required to dehumidify the inside of the apparatus completely prior to the XeF_2 -based silicon etching process.

10 Second, the XeF_2 -based etching may not be performed uniformly even on a full silicon wafer, because the etching occurs further in a portion having a denser XeF_2 gas on the surface of the silicon wafer than a portion with less dense XeF_2 gas. So, the etching uniformity depends on how the XeF_2 gas is uniformly distributed all over the surface of the target wafer.

15 Third, sublimation of the residual XeF_2 in the loading chamber may be problematic. It is general that the remaining XeF_2 after the etching process is reserved in the loading chamber for future uses, with the loading chamber maintained under vacuum according to the vacuum-based maintenance and control method. However, XeF_2 continuously sublimates in the loading chamber at the room temperature under a pressure less than 3.8
20 Torr. Such a sublimation of XeF_2 causes unnecessary consumption of an expensive material and association of the sublimated XeF_2 gas with air moisture to corrode the chamber and other connected, annexed parts.

Finally, it is hard to measure the amount of the residual XeF_2 in the loading chamber. The conventional XeF_2 -based silicon etching apparatus has a window on the loading

chamber for visual checking the amount of the residual XeF_2 in the chamber after the completion of the etching process. Such a visual check is a troublesome method and sometimes impossible when HF is formed from the sublimated XeF_2 associating with air moisture to corrode the window of the loading chamber cloudy.

5 Disclosure of Invention

The present invention is to solve the problems with the conventional XeF_2 -based silicon etching apparatus and it is therefore an object of the present invention to provide a XeF_2 -based silicon etching apparatus capable of eliminating the internal air moisture to minimize damages on a silicon oxide layer.

10 It is another object of the present invention to provide a XeF_2 -based silicon etching apparatus enabling uniform etching of a full silicon wafer.

If is further another object of the present invention to provide a XeF_2 -based silicon etching apparatus capable of preventing sublimation of the residual XeF_2 in a loading chamber.

15 It is still another object of the present invention to provide a XeF_2 -based silicon etching apparatus capable of measuring the amount of the residual XeF_2 in the loading chamber.

To achieve the above objects, there is provided a silicon etching apparatus using XeF_2 including: a basic structure composed of a loading chamber for loading XeF_2 , an
20 expansion chamber for collecting sublimated XeF_2 gas, and an etching chamber for performing an etching process; and a means for injecting nitrogen prior to the etching process to eliminate air moisture in the apparatus and thus preventing the formation of HF.

The silicon etching apparatus using XeF_2 further includes an injector having a predefined shape provided in the etching chamber for uniformly injecting the XeF_2 gas on

the surface of a wafer.

The silicon etching apparatus using XeF_2 further includes a feedback controller for feedback controlling the internal pressure of the loading chamber in order to prevent sublimation of the residual XeF_2 in the loading chamber.

- 5 The silicon etching apparatus using XeF_2 further includes a weight scale for measuring the weight of remaining XeF_2 in the loading chamber.

Brief Description of Drawings

Fig. 1 is a schematic diagram of a XeF_2 -based silicon etching apparatus according to an embodiment of the present invention;

- 10 ~~Fig. 2 and 3~~ show examples of a XeF_2 injector in an etching chamber contrived according to the present invention;

Fig. 4 is a schematic diagram of a feedback controller for maintaining the pressure of a loading chamber in the XeF_2 -based silicon etching apparatus of the present invention; and

- 15 Fig. 5 is a diagram of a weight scale in use, provided in the loading chamber of the XeF_2 -based silicon etching apparatus according to the present invention.

Preferred Embodiment for Carrying out the Invention

- Reference will now be made in detail to a XeF_2 -based silicon etching apparatus according to the present invention, examples of which are illustrated in the accompanying
20 drawings.

Fig. 1 is a schematic diagram of a XeF_2 -based silicon etching apparatus according to an embodiment of the present invention.

As shown in Fig. 1, the XeF_2 -based silicon etching apparatus of the present invention comprises a loading chamber 11, an expansion chamber 12, an etching chamber

13 and, further, a nitrogen injector for purging with nitrogen prior to the etching process to eliminate air moisture existing in the apparatus and thus, to prevent the formation of HF. Removal of HF raises the selectivity of silicon to masking oxide layers to more than 2000:1 to reduce damage to the masking oxide layers profile, enabling a long etching process.

5 The XeF_2 -based silicon etching apparatus of the present invention further comprises a XeF_2 injector having a predefined shape provided in the etching chamber 13 in order to provide uniformity in etching a full silicon wafer.

09644785-074200
10 Figs. 2 and 3 show examples of a XeF_2 injector in the etching chamber contrived according to the present invention. Figs. 2a and 3a are bottom views of the XeF_2 injector; Figs. 2b and 3b are side views; Figs. 2c and 3c are perspective views; and Figs. 2d and 3d show the XeF_2 injector during the etching step. As shown in Figs. 2 and 3, the XeF_2 injector of the present invention is contrived to uniformly inject XeF_2 from the top to the bottom in the etching chamber 13, thus creating a uniform downward viscous laminar motion of the XeF_2 gas. This is because the XeF_2 whose molecular weight is 169.29 g/mol is heavier than air (dry air, 28.96 g/mol) or nitrogen (28.0134 g/mol), and because in this
15 low pressure environment the downward flow becomes highly viscous.

20 The XeF_2 -based silicon etching apparatus of the present invention further comprises a means for maintaining the pressure of the loading chamber above 3.8 Torr and lower than the atmospheric pressure in order to prevent sublimation of the residual XeF_2 in the loading chamber which the etching apparatus is not use. With the internal pressure of the loading chamber lower than the atmospheric pressure, the cover of the loading chamber is maintained closed. In order to open the cover, the internal pressure of the loading chamber is increased to a pressure higher than the atmosphere pressure.

Fig. 4 is a schematic diagram of a feedback controller for maintaining the pressure

of the loading chamber 11 in the XeF_2 -based silicon etching apparatus of the present invention. As shown in Fig. 4, the feedback controller maintains, by way of feedback control, the internal pressure of the loading chamber 11 to a constant pressure between 3.8 Torr, which is the sublimation pressure of XeF_2 , and the atmospheric pressure. For this, the apparatus further comprises a pressure sensor 41 in the loading chamber 11 and uses a pressure gauge 42 to measure the internal pressure of the loading chamber 11, subtracting the measured pressure value from a reference pressure between the sublimation pressure of XeF_2 and the atmospheric pressure for feedback.

The XeF_2 -based silicon etching apparatus of the present invention further comprises a weight scale provided in the loading chamber 11 in order to measure the amount of the residual XeF_2 in the loading chamber 11.

Fig. 5 is a diagram showing the weight scale in use, provided in the loading chamber of the XeF_2 -based silicon etching apparatus according to the present invention. A container 51 filled with XeF_2 is placed on the weight scale 52 in the loading chamber 11 and the chamber 11 is made airtight. With the container 51 open, the weight of XeF_2 plus the container is measured, while measuring the weight of the residual XeF_2 in the loading chamber at any time during the etching step, to estimate the remaining time for performing the etching step with the residual XeF_2 .

As described in the above, the XeF_2 -based silicon etching apparatus of the present invention eliminates the inner air moisture to minimize a damage to an oxide layer and further comprises (a) the XeF_2 injector having a predefined shape in the etching chamber to enable uniform etching of a full silicon wafer, (b) the feedback controller for feedback controlling the pressure of the loading chamber above the sublimation pressure of XeF_2 and below the atmospheric pressure to prevent sublimation of the residual XeF_2 in the loading

chamber, and (c) the weight scale provided in the loading chamber to measure the amount of the residual XeF_2 .

[illegible]